
DURA+SKRIM® 2FR & 10FR

FIRE RETARDANT FOUR-LAYER REINFORCED LAMINATE



PRODUCT DESCRIPTION

DURA♦SKRIM® 2FR and 10FR consist of two sheets of highstrength fire-retardant virgin film laminated together with a third layer of molten polyethylene. A heavy-duty scrim reinforcement placed between these plies greatly enhances tear resistance and increases service life. DURA♦SKRIM's fire-retardant films meet or exceed NFPA's 701



test, method 2 (Large Scale Requirements).

PRODUCT USE

DURA SKRIM® 2FR and 10FR are used in applications that require a fire-retardant material, and demand high puncture and tear strengths.

SIZE & PACKAGING

DURA♦SKRIM® 2FR and 10FR are available in a variety of widths and lengths. Large pre-fabricated panel sizes up to 100,000 square feet are available. All panels are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time saving installation.



Building Abatement Enclosure

| PRODUCT | PART # |
|-----------------|--------|
| DURA♦SKRIM 2FR | R5CCF |
| DURA♦SKRIM 10FR | R10CCF |

APPLICATIONS

| Construction Enclosures | Temporary Walls | |
|-------------------------|--------------------|--|
| Asbestos Abatements | Curtains | |
| Fumigation Covers | Job Site Coverings | |

DURA-SKRIM®

DURA+SKRIM® 2FR & 10FR

FIRE RETARDANT FOUR-LAYER REINFORCED LAMINATE

| | | DURA ♦ SKRIM 2FR | | DURA+SKRIM 10FR | | |
|---|-------------------------|---|---|---|---|--|
| PROPERTIES | TEST METHOD | IMPERIAL | METRIC | IMPERIAL | METRIC | |
| Appearance | | Translucent, White Color | | Translucent, White Color | | |
| Thickness, Nominal | | 6 mil | 0.15 mm | 10 mil | 0.25 mm | |
| Weight | | 18.5 lbs/MSF 2.7 oz./yd ² | 90 g/m² | 40.5 lbs/MSF 5.8 oz./yd ² | 198 g/m² | |
| CONSTRUCTION | | Extrusion laminated with scrim reinforcement | | | | |
| ² 1" Tensile Strength | ASTM D7003 | 45 lbf/in | 79 N/cm | 57 lbf/in | 100 N/cm | |
| ² Elongation at Film Break | ASTM D7003 | 400 % | 400 % | 500 % | 500 % | |
| ² Grab Tensile | ASTM D7004 | 55 lbf | 245 N | 75 lbf | 334 N | |
| ¹ TRAPEZOID TEAR | ASTM D4533 | 30 lbf | 133 N | 44 lbf | 196 N | |
| Mullen Burst | ASTM D751 | 38 psi | 262 kPa | 75 psi | 517 kPa | |
| Maximum Static Use Temperature | | 180° F | 82° C | 180° F | 82° C | |
| Minimum Static Use Temperature | | -70° F | -57° C | -70° F | -57° C | |
| WVTR | ASTM E96 Procedure B | 0.587 grains/(100in ^{2.} day) | 0.590 g/(m ^{2.} day) | 0.214 grains/(100in ^{2.} day) | 0.202 g/(m ^{2.} day) | |
| Perm Rating | ASTM E96 Procedure B | 0.086 Perms grains/(ft ^{2.} hr·in Hg) | 0.057 Perms g/(24hr·m ² ·mm Hg) | 0.031 Perms grains/(ft ^{2.} hr·in Hg) | 0.021 Perms g/(24hr·m ² ·mm Hg) | |
| Burning Characteristics Flame Spread Index Smoked Developed Value | ASTM E84 Procedure A | 5 20 | | 5 55 | | |

¹ Tests are an average of diagonal directions.

² Tests are an average of primary reinforcement directions.

MEETS OR EXCEEDS THE FOLLOWING FIRE TESTING:

 National Fire Protection Association (NFPA) 701, Test Method 2 (Large Scale)
Class "A" Wall & Ceiling Finish Category as given in the National Fire Protection Association Life Safety Code 101, "Interior Wall and Ceiling Finish Classification" (ASTM E-84-97a).



DURA SKRIM® 2FR & 10FR are fire-retardant four-layer reinforced extrusion laminates. The outer layers consist of a high quality polyethylene film with a high concentration of fire-retardant additives. DURA SKRIM® 2FR & 10FR are reinforced with a heavy duty scrim laid in a diagonal pattern spaced 3/8" apart with an additional machine direction scrim every 9" (R5CCF) and 3" (R10CCF) across the width. The individual plies are laminated together with molten polyethylene. DURA SKRIM® 2FR & 10FR are designed to meet the stringent requirements of the Boston Fire Department for Temporary Enclosures.



download technical

data sheets.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. RAVEN INDUSTRIES MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.RavenEFD.com

RAVEN ENGINEERED FILMS P.O. Box 5107 Sioux Falls, SD 57117-5107 Ph: +1 (605) 335-0174 • TF: +1 (800) 635-3456

© 2016 RAVEN INDUSTRIES INC. All rights reserved.

efdsales@ravenind.com www.ravenefd.com



050316 EFD 1075